



WOOD FINISHES DIRECT

The following Technical Datasheet is provided by **Prestonett**

Wood Finishes Direct cannot be held liable for the information contained within this document.

For purchasing information visit:
[Prestonett Quick Dry Exterior Filler](#)

EXTERIOR QUICK DRY FILLER



GENERAL INFORMATION

Description

Powder quick-drying filler

Intended use

Exterior

- Filling holes and cracks of up to 4 cm
- Renovation work



PRODUCT ADVANTAGES

- + Easy to mix
- + Easy to apply
- + Excellent adhesion to substrates
- + Can be overcoated after just 3 hours
- + Does not shrink or crack
- + Water vapour permeable
- + Fibre enriched
- + White

USE

DILUTION

45% - i.e. 0.45 litre of water per 1 kg of powder

PREPARATION

Gradually pour the powder into water, stirring until a homogeneous paste is obtained.

APPLICATION

Conditions

Do not apply at temperatures of below +5°C or above +35°C, or at a relative humidity of above 80% H.R.

Equipment

Filling knife, blade.

Equipment cleaning

With water before completely dry. Do not throw away into drains, dispose of this material and its container to an approved disposal contractor or taken to municipal collection point. Do not dispose into the environment.

RECOMMENDATIONS

Do not apply in direct sunlight. Metallic reinforcement must be pre-treated with an appropriate product. Strip existing exterior polymer-based coatings and existing, poorly adhering substrates.

Dusty or soft substrates must be hardened before coating.

APPLICATION THICKNESS

4 cm

AVERAGE CONSUMPTION

0.9 kg of powder fills a volume of 1 litre

SUBSTRATES

Concrete, cellular concrete, cement, concrete block, brick, plaster, mortars, old painted substrates.

Substrates must be hard, cohesive, clean, sound and dry according to the local standards.


OVERCOAT

Exterior paint (thin film, thick plastic coating, waterproofing coating), epoxide, polyurethane.

EXTERIOR QUICK DRY FILLER



TECHNICAL DATA

| | |
|--|--|
| COMPONANTS | Cement base coat mix, organic binder, fibres, mineral fillers, additives. |
| pH | On mixing : 11 ± 1 After drying : 9 ± 1 |
| COLOUR | White |
| WORKING TIME AT 20°C | Approximately 35 minutes |
| WAITING TIME BEFORE OVERCOATING | Approximately 3 hours at 20°C – 55% H.R. (for 4 cm thickness) |
| CLASSIFICATION | NF T 36-005 - Family IV, class 4b |
| NORM | NF EN 16566 |
| V.O.C | < 0.5 g/l (Ready mixed) |
| HEALTH AND SAFETY |  <p>Danger - Contains cement Use in a well-ventilated place. Avoid direct contact with skin and eyes. Do not breathe dust. In case of prolonged contact, it is recommended to wear suitable gloves. Safety data sheet available on www.beissier.eu or www.quickfds.com</p> |
| PACKAGING | 2 kg, 1 kg box - 6 kg bag |
| STORAGE | 12 months from date of manufacture, in unopened original packaging, protected from frost, heat (max. +30°C), sun and moisture. Close well after use. Store in original packaging. |

This data sheet supersedes and replaces any prior sheet relating to the same product.

Date of issue : April 2017

The purpose of this data sheet is to inform our customers about our product's properties. The information presented in the sheet is based on the current state of our knowledge. However, this information is no substitute for a description pertaining specifically to the type and condition of the substrate concerned. Since technical progress is continuously being made, it is our customer's responsibility, prior to use, to check with us that updated edition of this sheet has not been issued.