

The following Technical Datasheet is provided by Craig and Rose

Wood Finishes Direct cannot be held liable for the information contained within this document.

For purchasing information visit: Craig And Rose Artisan Stainless Steel Effect

#### **TECHNICAL DATA SHEET**

TDS ART STAINLESS STEEL EFFECT 06/18 V1



940 - 7

## **ARTISAN** SPECIAL EFFECTS PAINTS

## **STAINLESS STEEL EFFECT**

Steel Metallic effect finish.   Apply by a Brush or Roller to create the effect of brushed Stainle Steel metal on trim areas, furniture and feature walls.   USES An internal decorative effect paint used to create the stylish look Stainless Steel.   COLOURS AVAILABLE 1 colours, Stainless Steel effect.   FINISH Sheen – Metallic TYPE REFERENCE NO. 940-7   NUMBER OF COMPONENTS One MIXING RATIO N/A				
Steel metal on trim areas, furniture and feature walls.   USES An internal decorative effect paint used to create the stylish look Stainless Steel.   COLOURS AVAILABLE 1 colours, Stainless Steel effect.   FINISH Sheen – Metallic TYPE REFERENCE NO. 940-7   NUMBER OF COMPONENTS One MIXING RATIO N/A   METHOD OF APPLICATION Roller or Brush – Use the brush in a random manner on final coal Can be sprayed.   AVAILABLE PACKS 125ml, 250ml.   SHEEN LEVEL A Stainless steel metallic effect finish.   PRACTICAL COVERAGE PER LITRE Approx. 1.5Sqm / 125ml & 3.0Sqm /250ml   FLASH POINT N/A Water based.   DRYING TIMES: SURFACE RECOAT 2-4 Hours   PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1 part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of	TYPE OF MATERIAL	Artisan Stainless Steel Effect is a water based paint with a Stainless Steel Metallic effect finish.		
Stainless Steel.   COLOURS AVAILABLE 1 colours, Stainless Steel effect.   FINISH Sheen – Metallic TYPE REFERENCE NO. 940-7   NUMBER OF COMPONENTS One MIXING RATIO N/A   METHOD OF APPLICATION Roller or Brush – Use the brush in a random manner on final coal Can be sprayed.   AVAILABLE PACKS 125ml, 250ml.   SHEEN LEVEL A Stainless steel metallic effect finish.   PRACTICAL COVERAGE PER LITRE Approx. 1.5Sqm / 125ml & 3.0Sqm /250ml   FLASH POINT N/A Water based.   DRYING TIMES: SURFACE   RECOAT 4 Hours   PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of				
FINISHSheen – MetallicTYPE REFERENCE No.940-7NUMBER OF COMPONENTSOneMIXING RATION/AMETHOD OF APPLICATIONRoller or Brush – Use the brush in a random manner on final coa Can be sprayed.Available packs125ml, 250ml.AVAILABLE PACKS125ml, 250ml.SHEEN LEVELA Stainless steel metallic effect finish.PRACTICAL COVERAGE PER LITREApprox. 1.5Sqm / 125ml & 3.0Sqm /250mlFLASH POINTN/A Water based.DRYING TIMES:SURFACE RECOATPREPARATIONRemove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of	USES	An internal decorative effect paint used to create the stylish look of Stainless Steel.		
NUMBER OF COMPONENTS   One   MIXING RATIO   N/A     METHOD OF APPLICATION   Roller or Brush – Use the brush in a random manner on final coal Can be sprayed.   AVAILABLE PACKS   125ml, 250ml.     AVAILABLE PACKS   125ml, 250ml.   SHEEN LEVEL   A Stainless steel metallic effect finish.     PRACTICAL COVERAGE PER LITRE   Approx. 1.5Sqm / 125ml   & 3.0Sqm /250ml     FLASH POINT   N/A Water based.     DRYING TIMES:   SURFACE   2-4 Hours     RECOAT   4 Hours     PREPARATION   Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1 part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of	COLOURS AVAILABLE	1 colours, Stainless Steel effect.		
METHOD OF APPLICATION Roller or Brush – Use the brush in a random manner on final coal Can be sprayed.   AVAILABLE PACKS 125ml, 250ml.   SHEEN LEVEL A Stainless steel metallic effect finish.   PRACTICAL COVERAGE PER LITRE Approx. 1.5Sqm / 125ml & 3.0Sqm /250ml   FLASH POINT N/A Water based.   DRYING TIMES: SURFACE   RECOAT 4 Hours   PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of	FINISH	Sheen – Metallic	TYPE REFERENCE NO.	940-7
Can be sprayed.   AVAILABLE PACKS 125ml, 250ml.   SHEEN LEVEL A Stainless steel metallic effect finish.   PRACTICAL COVERAGE PER LITRE Approx. 1.5Sqm / 125ml & 3.0Sqm /250ml   FLASH POINT N/A Water based.   DRYING TIMES: SURFACE   RECOAT 4 Hours   PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of	NUMBER OF COMPONENTS	One	MIXING RATIO	N/A
SHEEN LEVEL A Stainless steel metallic effect finish.   PRACTICAL COVERAGE PER LITRE Approx. 1.5Sqm / 125ml & 3.0Sqm /250ml   FLASH POINT N/A Water based.   DRYING TIMES: SURFACE   RECOAT 2-4 Hours   PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of	METHOD OF APPLICATION	Roller or Brush – Use the brush in a random manner on final coat. Can be sprayed.		
PRACTICAL COVERAGE PER LITRE Approx. 1.5Sqm / 125ml & 3.0Sqm /250ml   FLASH POINT N/A Water based.   DRYING TIMES: SURFACE   RECOAT 2-4 Hours   PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Near the solution of the surface should be primed with a coat of	AVAILABLE PACKS	125ml, 250ml.		
FLASH POINT N/A Water based.   DRYING TIMES: SURFACE RECOAT 2-4 Hours   PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of	SHEEN LEVEL	A Stainless steel metallic effect finish.		
DRYING TIMES: SURFACE 2-4 Hours   RECOAT 4 Hours   PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of	PRACTICAL COVERAGE PER LITRE	Approx. 1.5Sqm / 125ml & 3.0Sqm /250ml		
RECOAT 4 Hours   PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Neading patter, or porous surfaces should be primed with a coat of	FLASH POINT	N/A Water based.		
PREPARATION Remove loose or flaking paint, fill cracks or holes with filler and sand smooth. Abrade any silk, satin or glossy surfaces before painting over. Treat any mould with scouring pad and bleach solution (1part to 3 with water).leave on surface for 15minutes th wash with clean water and dry. Surfaces must be clean and dry free from grease oil or dirt or flaking coatings before painting. Ne dry plaster, or porous surfaces should be primed with a coat of				
	PREPARATION	sand smooth. Abrade any painting over. Treat any n solution (1part to 3 with w wash with clean water and free from grease oil or dir dry plaster, or porous surf	y silk, satin or glossy surfa nould with scouring pad a vater).leave on surface for d dry. Surfaces must be o t or flaking coatings befor faces should be primed w	aces before nd bleach r 15minutes then clean and dry and e painting. New rith a coat of

THIS INFORMATION IS GIVEN IN GOOD FAITH, BUT BECAUSE OF VARIATIONS IN APPLICATION AND USE, NO WARRANTY IS GIVEN OR IMPLIED REGARDING THE RESULTS OBTAINED. USERS SHOULD SATISFY THEMSELVES OF THE SUITABILITY FOR THEIR PURPOSE AND USE.

#### **TECHNICAL DATA SHEET**

TDS ART STAINLESS STEEL EFFECT 06/18 V1



940 - 7

# **ARTISAN** SPECIAL EFFECTS PAINTS

### **STAINLESS STEEL EFFECT**

Stir thoroughly prior to use. Before you begin, test your chosen application method on a large piece of board. Mask off adjacent walls skirting boards and cornices. Brush around the edges of the wall. Apply the first coat with a medium nap roller using light, even pressure. Take the roller as close to the edge as possible to cover the brush marks. Working in small sections, apply the second coat with a roller. While the paint is still wet, drag the brush in a random pattern. Best results are achieved by lightly brushing in one direction or reworking paint to achieve a brushed stainless steel effect. Make sure to overlap brushed areas to achieve an even effect. Avoid touching up. Spraying: On broad wall areas application by spray is recommended as this will give a more authentic look. Thin with 5% water if required. Apply 3-4 thin coats to achieve the desired effect and coverage. Thinning: Recommended for spraying only. Thin with 5% water.
Ensure the previous coat has fully dried for 4 hrs before over coating. Do not apply in temperatures near freezing as this will seriously slow down the drying and may destroy the structure of the paint. Store in a frost-free place and do not allow the paint to freeze. Do not apply to highly absorbant surfaces.
Remove as much paint as possible from equipment before cleaning with water. Clean hands with warm soapy water.
Ensure good ventilation during application and drying. After contact with skin, wash immediately with plenty of soap and water. In case of contact with the eyes, rinse immediately with plenty of water and seek medical advice. See can label for full instructions. Safety Data Sheets are available on request.
2004/42 EU Limit value for this product ( Cat A/I : 200g/L)
This product contains Max : 10g/L VOC.
Please dispose of unused paint and container responsibly. Do not empty into drains or watercourses. Some local authorities have

THIS INFORMATION IS GIVEN IN GOOD FAITH, BUT BECAUSE OF VARIATIONS IN APPLICATION AND USE, NO WARRANTY IS GIVEN OR IMPLIED REGARDING THE RESULTS OBTAINED. USERS SHOULD SATISFY THEMSELVES OF THE SUITABILITY FOR THEIR PURPOSE AND USE.

**TECHNICAL DATA SHEET** 

TDS ART STAINLESS STEEL EFFECT 06/18 V1



940 - 7

## **ARTISAN** SPECIAL EFFECTS PAINTS

### **STAINLESS STEEL EFFECT**

special facilities for the disposal of paint.

THIS INFORMATION IS GIVEN IN GOOD FAITH, BUT BECAUSE OF VARIATIONS IN APPLICATION AND USE, NO WARRANTY IS GIVEN OR IMPLIED REGARDING THE RESULTS OBTAINED. USERS SHOULD SATISFY THEMSELVES OF THE SUITABILITY FOR THEIR PURPOSE AND USE.